



LAMININ
COATINGS

for the next
generation

TECHNICAL DATA

AlUre Hydrophobic suede sheen acrylic.	
Date: February 2017/1	

<p>Product code: LAU001</p> <p>Colour: White, Pastel, Deep, Clear</p> <hr/> <p>Shelf life: 12 Months Packaging: 1ℓ, 5ℓ, 20ℓ Storage conditions: Store in a cool/dry place Stirring method: Stir with a flat paddle</p> <hr/> <p>Flashpoint: Non-flammable</p> <p>Viscosity: 100 - 110 KU (at 23°C) Specific weight: 1.15 - 1.32 Solids per volume: 30 - 36 % (Approx.) Solids per mass: 45 - 52 % (Approx.) Spreading rate: 8-10m²/1ℓ/coat Dry film thickness 20-30µm (Recommended) Wet film thickness 150µm VOC level ±3-4g/1ℓ White (Zero VOC)</p> <p>VOC Level will increase if not tinted with glycol free colourants.</p> <hr/> <p>Recommended coats: 2</p> <hr/> <p>Drying time: Touch Dry: 30min @ 23°C Dry to handle: 2h @ 23°C Overcoating: Minimum 2 hours @ 23°C</p> <hr/> <p>Application: Brush, roller and airless spray</p> <p>Cleaning: Water</p> <p>Scrubs: >10 000</p>	<p>GENERAL PREPARATIONS</p> <ul style="list-style-type: none"> ◦ All surfaces must be clean, sound and dry. ◦ Remove all loose flakes and apply PlasterSeal / PlasterPrime / WallPrime or BondAll, to obtain a stable surface. ◦ Smooth out imperfections with Skim and repair cracks with Fill. To stabilize chalky surfaces, apply PlasterSeal / PlasterPrime / WallPrime or BondAll, ◦ Previously painted sound surfaces can be washed with sugar soap and rinse thoroughly with clean water. ◦ To ease application, sand previously painted stable surfaces. ◦ For water damaged, porous and alkaline surfaces, apply WallPrime / PlasterPrime / BondAll or DampCure /, to stabilize surface. <p>FEATURES</p> <p>AlUre is based on an environmentally friendly, pure acrylic co-polymer emulsion that is APEO-, Ammonia-, Formaldehyde- and Iso-Thiazalone free. It dries to a beautiful suede sheen finish and features excellent flow- and levelling, - stain resistance, - washability and is virtually odourless for easy application. AlUre has superior hydrophobicity, - alkaline resistance, - UV stability, - flexibility and - dirt resistance. Formulated for interior and exterior use with anti mould and fungal technology.</p> <p>WHERE TO USE</p> <p>Walls and ceilings.</p>
---	---



QUALITY GUARANTEE: 15 Years

To qualify for quality guarantee, please register via our website or through your nearest distributor.

Terms and conditions apply – please consult the webpage for further information:
www.laminincoatings.co.za

PRECAUTIONS

- ° Avoid painting in moist / humid conditions. To allow applied paint to cure, there should be no rain forecast for at least 7 days.
- ° Do not paint over surfaces with moisture content above 15%. Ideal level 5% or less
- ° Stir paint well with a flat paddle.
- ° Ideal application conditions and surface temperature should be between 10°C - 35°C with a relative humidity of less than 75%. It is not recommended to paint in direct sunlight as this will result in the paint drying too fast leading to visible "lap-marks". Windy conditions might have a similar effect and can cause a deposit of dust particles on the wet paint.
- ° To ensure colour- and sheen level consistency, purchase from the same production batch of paint.
- ° Tint bases contain fewer litres than advertised.
- ° Spreading rates are theoretical and based on smooth / flat surfaces.
- ° Do not wash or abrade newly painted surfaces until properly cured.
- ° Allow 7 days for paint to dry properly and 30 days to reach full strength.
- ° Store paint in a cool, dry place.

HEALTH & SAFETY

- ° Keep out of children's reach.
- ° Do not eat, drink or smoke during any application.
- ° Ensure appropriate ventilation during application and drying.
- ° May be harmful if swallowed.
- ° Wear protective equipment during preparation, application and cleaning.
- ° Avoid contact with eyes.
- ° In case of contact, seek medical advice.
- ° Avoid contact with skin. In case of contact, wash thoroughly with appropriate solvent.
- ° If skin irritation occurs, seek medical advice.

Disclaimer:

- * Specifications and recommendations are given in good faith and are meant to be used as a guideline.
- * All information is based on results obtained from our tests done and experience gained over time.
- * Application method and - equipment, condition of substrate and - during application, will have an influence on results. This is beyond the manufacturer's control.
- * As technology may change over time, please ensure the use of the latest Technical Data Sheet.
- * All information listed is owned or used under licence of Laminin Coatings (Pty) Ltd and its related affiliates. © 2013 Laminin Coatings (Pty) Ltd. All rights reserved.