

# LAMININ

## Technical data sheet

Apr 2026/Is/Rev I

# RuBon

Liquid rubber  
High build, UV resistant  
waterproofing top coat





# Technical data sheet

**Product code:** LRB001  
**Colour:** Colours

**Shelf life:** 12 Months  
**Packaging:** 1l, 5l, 20l  
**Storage conditions:** Store in a cool/dry place  
**Stirring method:** Stir with a flat paddle

**Flashpoint:** **Non-flammable**

**Viscosity:** 106 – 112 KU (at 23°C)  
**Specific weight:** 1.25 – 1.30  
**Solids per volume:** 40 – 45 % (Approx.)  
**Solids per mass:** 52 – 56 % (Approx.)  
**Spreading rate:** 5m<sup>2</sup>/l/coat

Depending on porosity, surface conditions and application equipment  
**Dry film thickness** 100µm (Recommended)  
**Wet film thickness** 200µm

**Recommended coats:** 1-3

**Drying time:** Touch Dry: 2-4h @ 23°C

**Over coating:** Minimum 6-8 hours @ 23°C

**Application:** Airless Spray .25 tip, Brush or Roller  
Surface Temp 10 – 40°C  
Ambient Temp 5 – 35°C  
Relative Humidity 10 – 75 %

**Cleaning:** Water

## GENERAL PREPARATIONS

- All surfaces must be clean, sound & dry.
- Remove all loose flakes and apply **PlasterSeal** or **PlasterPrime** to obtain a stable surface.
- Smooth out plaster imperfections with **Skim**.
- Repair plaster cracks with premixed **Fill** or tile cement / plaster mix & **HydroKey**, diluted 50% with water.
- To stabilise chalky surfaces, apply **PlasterSeal** or **PlasterPrime**.
- Previously painted sound surfaces can be washed with sugar soap and rinsed thoroughly with clean water.
- To ease application, sand previously painted stable surfaces.
- Sand and remove varnish to bare surface.
- For water damaged, porous and alkaline surfaces, apply **PlasterPrime** or **DampCure** to stabilise surface.
- Remove rust from mild steel and galvanized substrates.
- Apply **HydroEtch** or **MSPrime** to stabilise surface.
- If rust cannot be removed completely, spot prime with a rust converter before applying **HydroEtch** or **MSPrime**.
- Before recoating, sand previously varnished surfaces well to remove mirror-like image to a flat film.
- Seal parapets in a criss-cross pattern with fibre reinforced **HydroFlex** or **RuBon**.
- Waterproof roofs with membrane in conjunction with **HydroSeal** or **RuBon**.
- **Tile and clay roofs** - apply one to two coats **BondAll** (Acrylic) until loose particles are thoroughly bonded.
- **Galvanized roofs** - apply a single coat **HydroEtch**.

## FEATURES

- UV-, mould- and fungal resistant rubberised topcoat for walls, roofs and parapets.
- Waterproofing primer, undercoat and topcoat with excellent ponding properties.
- Airless spray application for excellent flow and levelling.
- Dries to a high build smooth colourfast mid sheen finish to improve dust and dirt resistance.
- Formulated with activated zinc phosphate and flash rust inhibitor as anti-corrosive additives for long-term durability and stability.
- Prevents moisture ingress.
- Ideal for exterior areas exposed to direct moisture and high humidity.
- May be used with or without membrane.
- A maintenance coat is recommended every 3 – 5 years depending on colour and environmental conditions.

*Please be advised that rubber in this context refer to a flexible and high build dry film thickness.*

## WHERE TO USE

- Walls: suitably primed new and previously painted stable cement plaster, concrete and porous brickwork.
- Roofs: suitably primed new and previously painted stable galvanised, tile and clay roofs.



**LAMININ COATINGS** (PTY) LTD • Reg No 2012/103111/07

109 FRITZ STOCKENSTROM ST | NEW EAST END | BLOEMFONTEIN 9301



[www.laminincoatings.co.za](http://www.laminincoatings.co.za)



SINCE 1981



# Technical data sheet

## Application Details:

Pitch of Roof – Add % to spreading rate:

Depending on pitch, add 20 – 40 %

Type of Roof – Add % to spreading rate:

Corrugated & IBR – 20 - 25%

Smooth or granular cement tiles – 25 – 30%

Spreading Rate Calculations:

Granular cement tiles = 2 – 4m<sup>2</sup>/l/coat

Cement / Fibre cement tiles = 2 – 4m<sup>2</sup>/l/coat

Galvanised iron = 5m<sup>2</sup>/l/coat

Sealant for tiled roofs:

**BondAll** need to be applied to stabilise surface from all loose particles

## PRECAUTIONS

- Avoid painting in moist/humid conditions. To allow applied paint to cure, there should be no rain forecast for at least 7 days.
- Do not paint over surfaces with moisture content above 15% measured with an ultrasonic meter or over 5% with a pin type meter.
- Stir paint well with a flat paddle.
- Ideal application conditions and surface temperature should be between: 10°C - 35°C with a relative humidity of less than 75%. It is not recommended to paint in direct sunlight as this will result in the paint drying too fast leading to visible “lap-marks”. Windy conditions might have a similar effect and can cause a deposit of dust particles on the wet paint.
- To ensure colour– and sheen level consistency, purchase from the same production batch of paint. Touch-ups are not recommended.
- Tint bases contain fewer litres than advertised until tinted.
- Spreading rates are theoretical and based on smooth / flat surfaces.
- Do not wash or abrade newly painted surfaces until properly cured.
- Allow 7 days for paint to dry properly and 30 days to reach full strength.
- Store paint in a cool, dry place.
- Complies with the South African legal lead limit of 90ppm or less.

## COLOUR SELECTION

- Colours tinted that fall outside of Laminin Largo's formal tinting system may have risks regarding poor opacity, early fading, UV resistance, over and under tinting or alkaline attack. Please consult an official Laminin agent for advice.
- Do not alter factory standard colours as this will compromise the products longevity i.e. fading, UV and alkaline resistance, colour consistency and opacity.
- Bright colours plays an important role in colour selection, even though Laminin only makes use of lightfast pigments certain bright colours have a natural tendency for poorer opacity and UV resistance and might be more prone to alkaline attack. Please consult an official Laminin agent for the best possible advice.
- Colour variations due to efflorescence (White salty deposits) (alkaline burn or attack) will not be covered under early fading or product failure.
- The colour, white, may require a 3<sup>rd</sup> topcoat to achieve opacity and full obliteration.



**LAMININ COATINGS** (PTY) LTD • Reg No 2012/103111/07

109 FRITZ STOCKENSTROM ST | NEW EAST END | BLOEMFONTEIN 9301

**SABS**  
ISO 9001



[www.laminincoatings.co.za](http://www.laminincoatings.co.za)



SINCE 1981



## Technical data sheet

### HEALTH AND SAFETY

- Keep out of children's reach.
- Do not eat, drink or smoke during any application.
- Ensure appropriate ventilation during application and drying.
- Harmful if swallowed.
- Wear protective equipment during preparation, application and cleaning.
- Avoid contact with eyes. In case of contact, seek medical advice.
- Avoid contact with skin. In case of contact, clean with water.
- If skin irritation occurs, seek medical advice.

### QUALITY GUARANTEE

- **15 Years.** A maintenance coat is recommended every 3 – 5 years depending on colour (dark colours like Charcoal and Black) and environmental conditions (i.e. UV exposure).

To VALIDATE quality guarantee, please register via our website or through your nearest distributor.

### DISCLAIMER

- \* Specifications and recommendations are given in good faith and are meant to be used as guideline.
- \* All information is based on results obtained from our tests done and experience gained over time.
- \* Application method and - equipment, condition of substrate and - during application, will have an influence on results.
- \* This is beyond the manufacturer's control.
- \* As technology may change over time, please ensure the use of the latest Technical Data Sheet.
- \* All information listed is owned or used under licence of Laminin Coatings (Pty) Ltd and its related affiliates. © 2013 Laminin Coatings (Pty) Ltd. All rights reserved.

